

## Description

Lexan MR AC flame-retardant sheet is a two-side, hard-coated polycarbonate material offering excellent impact resistance, optical clarity and the state-of-the-art in abrasion and UV resistance. Lexan MR AC sheet is specifically designed for aircraft window dust covers, acoustical panels, visors, diffusers, and any other similar application not requiring forming.

## Typical Property Values ♦

Property	Test Method	Unit	Value
<b>Physical</b>			
Specific Gravity (color dependent)	ASTM D792	-	1.20 – 1.27
Water Absorption, Equilibrium, 24 hrs.	ASTM D570	%	0.2
Sound Transmission (STC Ratings 36"x84") @ .125"	ASTM E9070	-	25
@ .187"			29
Abrasion Resistance, CS10F wheels, 500 gram load, 100 cycles	ASTM D1044-76	%	1-4
<b>Mechanical</b>			
Tensile Strength @ Yield			10,000
Ultimate			9,500
Tensile Modulus	ASTM D638	psi	245,000
Tensile Elongation, Ultimate	ASTM D638	%	>80
Flexural Strength (Gauge Dependent)#	ASTM D790	psi	14,000
Flexural Modulus (Gauge Dependent)#	ASTM D790	psi	350,000
Dynatup Impact Strength, 1/2" dia. dart (Gauge Dependent)# @ 73°F	ASTM D3763	ft-lbs	50
Izod Impact Strength (Gauge Dependent)# Notched @ 73°F	ASTM D256A	ft-lbs/in	2.4
Unnotched @ 73°F			NB
Gardner Impact Strength, round tup (Gauge Dependent)# @ 73°F	ASTM D3029	in-lbs	>320
<b>Thermal</b>			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 <sup>-5</sup>
Heat Deflection Temperature @ 264 psi	ASTM D648	°F	270
<b>Flammability</b>			
FAA Flammability @ .060" to .500"	FAR 25.853F1AI/ BSS 7230	-	Pass

- ♦ These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics' representative.
- Trademark of SABIC Innovative Plastics IP BV
- # Reported values based on 0.118" gauge thickness



\* Trademark of SABIC Innovative Plastics IP BV



**ООО «Торгово-Строительная Компания Империя»**

109382, Россия, г.Москва, ул.Нижние поля, 31  
+7(495)646-81-65  
info@tbc-empire.ru  
www.tbc-empire.ru

**LLC TBC Empire**

109382, Russia, Moscow, Nizhniye polya,31  
+7(495)646-81-65  
info@tbc-empire.ru  
www.tbc-empire.ru

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

\* Trademark of SABIC Innovative Plastics IP BV